

Product Description

Panacol Elecolit[®] adhesives are solvent free single or two-component adhesives. They are mostly based on epoxy resin and can be cured at room temperature or by exposure of heat. Elecolit[®] adhesives are electrically and / or thermally conductive adhesives which are designed for potting, bonding or contacting of conductors.

Elecolit[®] 3661 is a single part silver filled conductive adhesive. The product does not contain any solvents and the open pot life time will be 14 days and longer.

The slightly flexibilized polymer structure allows to use Elecolit[®] 3661 in applications that are subject to vibrations or quick temperature fluctuations. The high viscosity of this product makes it possible to apply the material via dispenser, stamping or pin transfer without tailing effects.

Elecolit[®] 3661 will cure rapidly by exposure of heat. For good conductivity and resistivity we recommend a curing time of approx. 10min at 150°C.

Curing Properties

The product is a one-component adhesive and can be cured with the addition of heat. Possible curing temperatures are listed in the table below.

Thermal curing	[min]
Time at 80°C	360
Time at 110°C	45
Time at 120°C	30
Time at 130°C	15
Time at 150°C	10

The curing times given are guidelines. They refer to the curing of 2 g of adhesive. The heating up of the joining members are not taken into account.

The final strength of the adhesive is reached at the earliest after 24 h.

Technical Data

Resin	epoxy
Appearance	grey
Filler	silver
Filler – weight [%]	71
Particle size D100 [µm]	18

Uncured material

Viscosity [mPas] (Bohlin CVO, 25°C, 10,5s ⁻¹) <i>PE-Norm 029</i>	20 000 - 40 000
Density [g/cm ³] <i>PE-Norm 004</i>	2,6
Flash point [°C] <i>PE-Norm 050</i>	>100

Cured material

Hardness shore D <i>PE-Norm 006</i>	70 - 80
Temperature resistance [°C] <i>PE-Norm 065</i>	-40 - 180
Water absorption [mass %] <i>PE-Norm 016</i>	0,30

Glass transition temperature DSC [°C] <i>PE-Norm 009</i>	90 - 130
Coefficient of linear expansion [ppm/K] below T _g <i>PE-Norm 017</i>	70,00
Coefficient of linear expansion [ppm/K] above T _g <i>PE-Norm 017</i>	220,00

Volume resistivity [Ohm*cm] <i>PE-Norm 040</i>	5,00E-03
---	----------

Lap shear strength (Al/Al) [MPa] <i>PE-Norm 013</i>	4,4
Lap shear strength (steel/steel) [MPa] <i>PE-Norm 013</i>	4,8

Transport/Storage/Shelf Life

Trading unit	Transport	Storage	Shelf-life*
Cartridge	0°C - 10°C	0°C - 10°C	At delivery min. 2 months, max. 4 months
Other packages			

***Store in original, unopened containers!**

Instructions for Use

Surface preparation

The surfaces to be bonded should be free of dust, oil, grease or other dirt in order to obtain an optimal and reproducible bond.

For cleaning we recommend the cleaner IP[®] Panacol. Substrates with low surface energy (e.g. polyethylene, polypropylene) must be pretreated in order to achieve sufficient adhesion.

Application

Our products are supplied ready to use. Depending on packaging they can be applied by hand directly from the container or semi or fully automatically. With automated application from the cartridge the adhesive is conveyed by a compressed air-operated displacement plunger via a valve in the needle. When metering low viscosity materials from bottles the adhesive is transported by a diaphragm valve. If help is required, please contact our application engineering department.

Adhesive and substrate may not be cold and must be warmed up to room temperature prior to processing.

For safety information refer to our safety data sheet.

Note

The product is free of heavy metals, PFOS and Phthalates and is conform to the EU-Directive 2011/65/EU "RoHS II" .

Our data sheets have been compiled to the best of our knowledge. The enclosed information describes characteristic properties, with no declaration of commitment. We recommend trials in order to confirm that our products satisfy the particular application requirements. For any additional technical support, please contact our application engineering department. For warranty claims, please refer to our standard terms and conditions.