

# Technical Datasheet

## Structalit® 8801 T



° Preliminary Datasheet. The technical statements are only guidelines and can be changed at any time.

### Product Description

Panacol Structalit® adhesives are solvent free single or two-component adhesives. They are mostly based on epoxy resin and can be cured at room temperature or by exposure of heat. Structalit® products are designed for bonding, casting and protecting components in electronic and automotive industry.

Structalit® 8801 T is a universal one component epoxy adhesive which can also be used as a potting compound. Structalit® 8801 T is characterized by short curing times at low temperatures. Processing temperatures should be above 20 ° C to simplify the application.

Structalit® 8801 T has a very good oil resistance and is qualified for applications in automotive and aerospace industry.

#### Suitability on various substrates

PA	✓	Al	✓	glass	✓	brass	✓
PC	o	copper	✓	steel	✓	ceramic	✓

✓excellent    o suitable    \* pretreatment necessary/recommended

### Curing Properties

The product is a one-component adhesive and can be cured with the addition of heat. Possible curing temperatures are listed in the table below.

Thermal curing	[min]
Time at 100°C	9
Time at 130°C	6
Time at 150°C	5

The curing times given are guidelines. They refer to the curing of 2 g of adhesive. The heating up of the joining members are not taken into account.

The final strength of the adhesive is reached at the earliest after 24 h.

### Technical Data

Resin	epoxy
Appearance	beige
Filler	chalk
Filler – weight [%]	30
Particle size D98 [µm]	12,5

° Preliminary Datasheet. The technical statements are only guidelines and can be changed at any time.

### Uncured material

Viscosity [mPas] (Kinexus Rheometer, 25 °C, 5 <sup>s-1</sup> ) <i>PE-Norm 064</i>	20 200
Viskosity [mPas] (Kinexus Rheometer, 25 °C, 5 <sup>s-1</sup> ) <i>PE-Norm 064</i>	12 600
Density [g/cm <sup>3</sup> ] <i>PE-Norm 004</i>	1,4
Flash point [°C] <i>PE-Norm 050</i>	>100

### Cured material

Hardness shore D <i>PE-Norm 006</i>	74,0
Temperature resistance [°C] <i>PE-Norm 065</i>	-40 - 200
Shrinkage [%] <i>PE-Norm 031</i>	<0,1
Volume Shrinkage [%] <i>PE-Norm 032</i>	6,1
Water absorption [mass %] <i>PE-Norm 016</i>	0,5

Glass transition temperature DSC [°C] <i>PE-Norm 009</i>	112,0
Coefficient of linear expansion [ppm/K] below Tg <i>PE-Norm 017</i>	40,0
Coefficient of linear expansion [ppm/K] above Tg <i>PE-Norm 017</i>	170,0

Young's modulus E [MPa] <i>PE-Norm 056</i>	16 000
Tensile strength [MPa] <i>PE-Norm 014</i>	12,6
Elongation at break [%] <i>PE-Norm 014</i>	0,13
Lap shear strength (Al/Al) [MPa] <i>PE-Norm 013</i>	11,0
Lap shear strength (Messing/Messing) [MPa] <i>PE-Norm 013</i>	13,0
Lap shear strength (Stahl/Stahl) [MPa] <i>PE-Norm 013</i>	16,0

° Preliminary Datasheet. The technical statements are only guidelines and can be changed at any time.

### Transport/Storage/Shelf Life

Trading unit	Transport	Storage	Shelf-life*
Cartridge	0°C - 10°C	0°C - 10°C	at delivery min. 3 months max. 6 months
Other packages			

**\*Store in original, unopened containers!**

### Instructions for Use

#### Surface preparation

The surfaces to be bonded should be free of dust, oil, grease or other dirt in order to obtain an optimal and reproducible bond.

For cleaning we recommend the cleaner IP® Panacol. Substrates with low surface energy (e.g. polyethylene, polypropylene) must be pretreated in order to achieve sufficient adhesion.

#### Application

Our products are supplied ready to use. Depending on packaging they can be applied by hand directly from the container or semi or fully automatically. With automated application from the cartridge the adhesive is conveyed by a compressed air-operated displacement plunger via a valve in the needle. When metering low viscosity materials from bottles the adhesive is transported by a diaphragm valve. If help is required, please contact our application engineering department.

Adhesive and substrate may not be cold and must be warmed up to room temperature prior to processing.

For safety information refer to our safety data sheet.

### Note

The product is free of heavy metals, PFOS and Phthalates and is conform to the EU-Directive 2011/65/EU "RoHS II" .

Our data sheets have been compiled to the best of our knowledge. The enclosed information describes characteristic properties, with no declaration of commitment. We recommend trials in order to confirm that our products satisfy the particular application requirements. For any additional technical support, please contact our application engineering department. For warranty claims, please refer to our standard terms and conditions.