

Technical Datasheet

Vitralit® UD 8050



° Preliminary Datasheet. The technical statements are only guidelines and can be changed at any time.

Product Description

Panacol Vitralit® adhesives are one-component, solvent-free radiation-curing adhesives. The advantages are very short curing time, good adhesion to a variety of substrates, and easy handling. Vitralit® products are used in electronics, medical applications, optics and for fixing parts in general.

Vitralit® UD 8050 is a one component UV/visible light and humidity curing isocyanate acrylate adhesive. The base material is transparent and slightly yellow. Customized versions with various colors and fluorescent tracer are possible and make process control easier.

Vitralit® UD 8050 is specially designed as an encapsulant for local circuit board protection. Its easy dispensability and fast curing properties make it suitable especially for applications in consumer electronics, where a high UPH value is required. Thanks to the humidity curing mechanism, Vitralit® 8050 can also be cured in shadowed areas. UV curing provides initial properties and the humidity post curing leads to an increasing performance over time.

Curing Properties

UV-A	VIS	Thermal curing	Humidity curing
✓	✓	-	✓

✓ suitable - not suitable

The product cures within seconds with radiation in the UV-A - (320 nm - 390 nm) and visible range (405nm). For rapid and high quality crosslinking we recommend the UV devices manufactured by Dr. Hoenle AG, which complement our adhesive technology.

In shadowed areas, it can be cured through environmental humidity (20 % - 80 % RH recommended). Post cure by humidity leads to an increasing bonding strength over time. Final bonding strength is achieved after approximately one week.

Bluepoint LED/LED-spot		
Wavelength [nm]	365	405
Suitability	++	+++

+ application-related ++ well-suited +++ ideal - not suitable

To obtain full cure at least one substrate must be transparent to recommended wavelength for cure. The curing speed will depend on the intensity of light, light source, the exposure time, and the light transmittance of the substrate.

Curing with UV and LED devices from Dr. Hönle AG		
Curing unit	Intensity [mW/cm²]	Curing time * [sec]
LED Spot 100, 405 nm	250	3
LED Spot 100, 365 nm	200	2
UVA Lamp, Fe-doped	60	5

* Curing time for material with a thickness of 0.5 mm. For thicker adhesive layer more time is necessary.

Please note that UV cure only provides initial bonding strength and the humidity post cure leads to an increasing bonding strength and Shore hardness over time.

Technical Datasheet

Vitralit® UD 8050



° Preliminary Datasheet. The technical statements are only guidelines and can be changed at any time.

Technical Data

Resin isocyanate acrylate
 Appearance transparent, slightly yellow

Uncured material

Viscosity [mPas] (Kinexus Rheometer, 5s ⁻¹ , 25°C) <i>PE-Norm 064</i>	9 500
Viscosity [mPas] (Kinexus Rheometer, 50s ⁻¹ , 25°C) <i>PE-Norm 064</i>	2 600
Density [g/cm ³] <i>PE-Norm 004</i>	1,1
Flash point [°C] <i>PE-Norm 050</i>	>100

Cured material

	Shore Hardness D	Bonding Strength (N per Die)*
Initial, after UV cure**	15	22
+ 1 day humidity cure***	22	37
+ 2 days humidity cure	40	96
+ 3 days humidity cure	50	102
+ 4 days humidity cure	56	122
+ 5 days humidity cure	60	131
+ 6 days humidity cure	63	140
+ 7 days humidity cure	64	143
+ 8 days humidity cure	64	142

*Ceramic resistance die 1206 (3.2mm x 1.6mm). The ceramic die which has no light transmission is bonded to PCB with solder mask, UV only cures the adhesive on edge and fixes the die. The adhesive under the die is then cured with humidity over time.

**UV cure: UVA lamp, Fe-doped, 60 mW/cm², 30 s.

*** Humidity cure: 25 °C, 50 % RH.

Temperature resistance [°C] <i>PE-Norm 065</i>	-40 - 120
Shrinkage [%] <i>PE-Norm 031</i>	2,0

Technical Datasheet

Vitralit® UD 8050



° Preliminary Datasheet. The technical statements are only guidelines and can be changed at any time.

Glass transition temperature DSC [°C] (UV + 7 days humidity cure @ 25 °C, 50 % RH) PE-Norm 009	64
Coefficient of linear expansion [ppm/K] above Tg (UV + 7 days humidity cure @ 25 °C, 50 % RH) PE-Norm 017	282
Coefficient of linear expansion [ppm/K] below Tg (UV + 7 days humidity cure @ 25 °C, 50 % RH) PE-Norm 017	70

Transport/Storage/Shelf Life

Trading unit	Transport	Storage	Shelf-life*
Cartridge	0°C - 10°C	0°C - 10°C	At delivery min. 3 months, max. 6 months
Other packages			

***Store in original, unopened containers!**

Instructions for Use

Surface preparation

The surfaces to be bonded should be free of dust, oil, grease or other dirt in order to obtain an optimal and reproducible bond.

For cleaning we recommend the cleaner IP® Panacol. Substrates with low surface energy (e.g. polyethylene, polypropylene) must be pretreated in order to achieve sufficient adhesion.

Application

Our products are supplied ready to use. Depending on packaging they can be applied by hand directly from the container or semi or fully automatically. With automated application from the cartridge the adhesive is conveyed by a compressed air-operated displacement plunger via a valve in the needle. When metering low viscosity materials from bottles the adhesive is transported by a diaphragm valve. If help is required, please contact our application engineering department.

Adhesive and substrate may not be cold and must be warmed up to room temperature prior to processing.

After application, bonding of the parts should be done quickly. Vitralit® adhesives cure slowly in daylight. Therefore, we recommend to expose the material to as little light as possible and the use of opaque hose lines and dispensing needles.

For safety information refer to our safety data sheet.

Technical Datasheet

Vitralit[®] UD 8050



° Preliminary Datasheet. The technical statements are only guidelines and can be changed at any time.

Note

The product is free of heavy metals, PFOS and Phthalates and is conform to the EU-Directive 2011/65/EU "RoHS II" .

Our data sheets have been compiled to the best of our knowledge. The enclosed information describes characteristic properties, with no declaration of commitment. We recommend trials in order to confirm that our products satisfy the particular application requirements. For any additional technical support, please contact our application engineering department. For warranty claims, please refer to our standard terms and conditions.