

### **Product Description**

Modified acrylate | 1 part | thermal curing | thermally conductive | electrically conductive

- Contacting rear window heaters
- Coating
- ESD protective lacquer

- Silver-filled
- Good adhesion to glass, metal and plastic
- Contains solvent

### **Curing Properties**

This adhesive can be cured at room temperature or more rapidly with heat. Typical curing temperatures are listed in the table below.

Temperatures	Time
25°C	12 h
50°C	2 h
100°C	30 min
120°C	10 min

The heat cure times are only provided as a guideline. They are derived from curing a 2g adhesive sample without affixed substrates in a laboratory environment. Actual cure times can vary based on part size, configuration, adhesive volume, temperature control, and the time required for the component substrates to attain oven temperature.



Technical Data		
Resin	Acrylate	
Appearance	Grey	
Filler	Silver	
Filler - weight [%]	75	
Particle size D95 [µm]	10	
Uncured Material		
Viscosity [mPas] (Kinexus Rheometer, 25 °C, 10s <sup>-1</sup> )	1,000 – 2,000	
PE-Standard 064	2,000 2,000	
Density [g/cm <sup>3</sup> ]	2.0 - 3.0	
PE-Standard 004	2.0 0.0	
Working life [h]	1	
@ room temperature		
Cured Material		
Temperature resistance [°C]	-60 – 175	
Water absorption [%]	. 1	
PE-Standard 016	<1	
Thermal conductivity [W/m*K]	1.8 - 2.2	
PE-Standard 062	1.8 - 2.2	
Volume resistivity [Ohm*cm]	1E-3 – 1E-2	
PE-Standard 040	12-3 - 12-2	

# Transport/Storage/Shelf Life

Package type	Transport	Storage	Shelf life*
Syringe/Cartridge	At room temperature max. 25°C	0°C – 10°C	At delivery min. 6 months
Other packages		0 C = 10 C	max. 12 months

\*Store in original, unopened containers!



### Instructions for use

After storing the container at 0°C - 10°C, Elecolit<sup>®</sup> 342 must be homogenized because of possible sedimentation of silver.

### Surface preparation

The surfaces to be bonded should be free of dust, oil, grease, mold release, or other contaminants in order to obtain an optimal and reproducible bond. For cleaning we recommend the cleaner IP<sup>®</sup> from Panacol, or a solution of Isopropyl Alcohol at 90% or higher concentration. Substrates with low surface energy (e.g. polyethylene, polypropylene) must be pretreated in order to achieve sufficient adhesion.

### Application

Our products are supplied ready to use. Depending on the packaging, our adhesives may be dispensed by hand directly from the package, or they can be applied using dispensing systems and automation. Many commercially available valve and controller options are available to ensure accurate and consistent adhesive dispensing. For assistance with dispensing and curing questions, please contact our Applications Engineering department. Adhesive and substrate should not be cold for proper bonding. They must be allowed to warm to room temperature prior to processing. After curing, the adhesive must be allowed to cool to ambient temperature before testing the product's performance. For safety information refer to our Material Safety Data Sheet (MSDS).

#### Storage

Store uncured product in its original, closed container in a dry location. Any material removed from the original container must not be returned to the container as it could be contaminated. Panacol cannot assume responsibility for products that were improperly stored, contaminated, or repackaged into other containers.

#### Handling and Clean-up

For safe handling information, consult this product's Material Safety Data Sheet (MSDS) prior to use. Uncured material may be wiped away from surfaces with organic solvents. Do not use solvents to remove material from eyes or skin!



#### Disclaimer

The product is free of heavy metals, PFOS and Phthalates and is conform to the current EU-Directive RoHS.

## THE VALUES NOTED IN THIS TECHNICAL DATA SHEET ARE TYPICAL PROPERTIES AND ARE NOT MEANT TO BE USED AS PRODUCT SPECIFICATIONS.

The information contained in this data sheet is believed to be accurate and is provided for information only. Panacol makes no representation or warranties of any kind concerning this information. It is the user's responsibility to determine the suitability of this product for any intended use. Panacol does not assume responsibility for test or performance results obtained by the user. The user assumes all risk and liability connected with the use of this product.

The user should adopt such precautions and use guidelines as may be advisable for the protection of property and persons against any hazards that may be involved in this product's handling or use. Panacol specifically disclaims any liability for consequential or incidental damages of any kind arising from the handling or use of this product. The information contained in this Technical Data Sheet offers no assurance that the product use, application, or process will not infringe on existing patents or licenses of others. Nothing in this Technical Data Sheet transfers or grants license for the use of any patents, trade secrets, intellectual property, or confidential information that is the property of Panacol.

Except as otherwise noted, all trademarks in this document (identified as <sup>®</sup>) are the property of Panacol.

Contact

Panacol-Elosol GmbH Stierstädter Straße 4 61449 Steinbach Germany Phone: +49 6171 6202-0 Mail: info@panacol.de www.panacol.com Panacol-USA, Inc. 142 Industrial Lane Torrington CT 06790 USA Phone: +1 860-738-7449 Mail: info@panacol-usa.com www.panacol-usa.com Panacol-Korea Co., Ltd. #707, Kranz Techno, 388 Dunchon-daero Junwon-gu, Seongnam Gyeonggi-do, 13403 KOREA Phone: +82 31 749 1701 Mail: info@panacol-korea.com www.panacol-korea.com Eleco Panacol – EFD 125, av Louis Roche Z.A. des Basses Noëls 92238 Gennevilliers Cdx FRANCE Tél.: +33 (0)1 47 92 41 80 Mail: eleco@eleco-panacol.fr www.eleco-panacol.fr

> Page 4/4 Updated 10.12.2024 Revision: 4 DIN ISO 9001 certified