

# Technical Datasheet

## Structalit® 8202



° Preliminary Datasheet. The technical statements are only guidelines and can be changed at any time.

### Product Description

Panacol Structalit® adhesives are solvent free single or two-component adhesives. They are mostly based on epoxy resin and can be cured at room temperature or by exposure of heat. Structalit® products are designed for bonding, casting and protecting components in electronic and automotive industry.

Structalit® 8202 is a classical underfill material designed for chip stack packages and BGA. It is one part black colored epoxy and cures rapidly under the influence of heat. Special feature of this product is the low viscosity, good capillarity, low coefficient of thermal expansion and the high glass transition-level. It is designed to cure quickly at moderate temperatures to minimize stress to other components. Due to its good compatibility with most Pb-free solders, the cured material can provide excellent mechanical properties to protect solder joints during thermal cycling. The underfiller can also be cured in the reflow process. Curing temperature and time could be optimized by customers in their own processes. This product is in full compliance with RoHS and halogen free (electronic grade).

### Curing Properties

The product is a one-component adhesive and cures under exposure to heat. Possible curing temperatures are listed in the table below.

Thermal curing	[min]
Time at 130°C*	10

\* object temperature

The curing times given are guidelines. They refer to the curing of 2 g of adhesive. The heating up of the joining members are not taken into account.

The final strength of the adhesive is reached at the earliest after 24 h.

### Technical Data

Resin epoxy  
Appearance black

#### Uncured material

Viscosity [mPas] (Kinexus Rheometer, 25°C, 60s <sup>-1</sup> ) <i>PE-Norm 064</i>	330
Density [g/cm <sup>3</sup> ] <i>PE-Norm 004</i>	1,15
Pot life @ 25 °C [days] 25 % viscosity increase	3
Flash point [°C] <i>PE-Norm 050</i>	>100

# Technical Datasheet

## Structalit® 8202



° Preliminary Datasheet. The technical statements are only guidelines and can be changed at any time.

### Cured material

Hardness shore D <i>PE-Norm 006</i>	74
Temperature resistance [°C]	-40 - 200
Water absorption [mass %] <i>PE-Norm 016</i>	<1

Glass transition temperature DSC [°C] <i>PE-Norm 009</i>	93
Coefficient of thermal expansion [ppm/K] below Tg <i>PE-Norm 017</i>	15
Coefficient of thermal expansion [ppm/K] above Tg <i>PE-Norm 017</i>	167

Dielectric constant [1MHz]	1,6
Dielectric loss factor [1MHz]	8,31*E-3

Young's modulus E [MPa] <i>PE-Norm 056</i>	2 519
Young's modulus E [MPa] <i>DMA-measurement</i>	1 150
Tensile strength [MPa] <i>PE-Norm 014</i>	45
Elongation at break [%] <i>PE-Norm 014</i>	2

### Transport/Storage/Shelf Life

Trading unit	Transport	Storage	Shelf-life*
Cartridge	0°C - 10°C	-20°C	at delivery max. 3 months
Other packages			

**\*Store in original, unopened containers!**

### Instructions for Use

#### Surface preparation

The surfaces to be bonded should be free of dust, oil, grease or other dirt in order to obtain an optimal and reproducible bond.

For cleaning we recommend the cleaner IP® Panacol. Substrates with low surface energy (e.g. polyethylene, polypropylene) must be pretreated in order to achieve sufficient adhesion.

# Technical Datasheet

## Structalit® 8202



° Preliminary Datasheet. The technical statements are only guidelines and can be changed at any time.

### Application

Our products are supplied ready to use. Depending on packaging they can be applied by hand directly from the container or semi or fully automatically. With automated application from the cartridge the adhesive is conveyed by a compressed air-operated displacement plunger via a valve in the needle. When metering low viscosity materials from bottles the adhesive is transported by a diaphragm valve. If help is required, please contact our application engineering department.

Adhesive and substrate may not be cold and must be warmed up to room temperature prior to processing.

For safety information refer to our safety data sheet.

### **Disclaimer**

The product is free of heavy metals, PFOS and Phthalates and is conform to the EU-Directive 2017/2102/EU "RoHS III".

**THE VALUES NOTED IN THIS TECHNICAL DATA SHEET ARE TYPICAL PROPERTIES AND ARE NOT MEANT TO BE USED AS PRODUCT SPECIFICATIONS.**

The information contained in this data sheet is believed to be accurate and is provided for information only. Panacol makes no representation or warranties of any kind concerning this information. It is the user's responsibility to determine the suitability of this product for any intended use. Panacol does not assume responsibility for test or performance results obtained by the user. The user assumes all risk and liability connected with the use of this product.

The user should adopt such precautions and use guidelines as may be advisable for the protection of property and persons against any hazards that may be involved in this product's handling or use. Panacol specifically disclaims any liability for consequential or incidental damages of any kind arising from the handling or use of this product. The information contained in this Technical Data Sheet offers no assurance that the product use, application, or process will not infringe on existing patents or licenses of others. Nothing in this Technical Data Sheet transfers or grants license for the use of any patents, trade secrets, intellectual property, or confidential information that is the property of Panacol.

Except as otherwise noted, all trademarks in this document (identified as ®) are the property of Panacol.

### Contact

**Panacol-Elosol GmbH**  
Daimlerstr. 8  
61449 Steinbach  
Germany  
Phone.: +49 6171 6202-0  
Mail: [info@panacol.de](mailto:info@panacol.de)  
[www.panacol.com](http://www.panacol.com)

**Panacol-USA, Inc.**  
142 Industrial Lane  
Torrington CT 06790  
USA  
Phone: +1 860-738-7449  
Mail: [info@panacol-usa.com](mailto:info@panacol-usa.com)  
[www.panacol-usa.com](http://www.panacol-usa.com)

**Panacol-Korea Co., Ltd.**  
#707, Kranz Techno, 388 Dunchon-daero  
Junwon-gu, Seongnam  
Gyeonggi-do, 13403 KOREA  
Phone: +82 31 749 1701  
Mail: [info@panacol-korea.com](mailto:info@panacol-korea.com)  
[www.panacol-korea.com](http://www.panacol-korea.com)

**Eleco Panacol – EFD**  
125, av Louis Roche  
Z.A. des Basses Noëls  
92238 Gennevilliers Cdx FRANCE  
Tél.: +33 (0)1 47 92 41 80  
Mail: [eleco@eleco-panacol.fr](mailto:eleco@eleco-panacol.fr)  
[www.eleco-panacol.fr](http://www.eleco-panacol.fr)